



Explication du test inter-laboratoires international du CSITC



Gourlot J.-P.
UR 102 - LTC

Explic_CSITC_InaugurationRTC_Courte_V0.ppt



Plan of presentation Plan de présentation



- Existing tests
- CSITC RT
- Data for one instrument
- Evaluation principle
- Charts
- Influences
- Example
- Another example
- On the long run
- Tests actuels
- CSITC RT
- Données d'un instrument
- Principe d'évaluation
- Graphes
- Influences
- Exemple
- Autre exemple
- Dans le temps



This project is co-funded by
the European Union and the
Common Fund for Commodities

Existing Round Trials – Attributes

(1)

Critères des tests existants



Attribute	USDA HVI Checktest	Bremen Round Trial	CSITC Round Trial
Number of participants	50 to 80 HVIs	100 to 120 HVIs	60 to 80 HVIs increasing
Start	?	1950s	2007
Region	Worldwide	Worldwide	Worldwide
Kinds of instruments	High Volume Testing	All kinds	High Volume Testing
Costs for participation	Charged	Free	Subsidized charge
Cottons: Origin and type	USA; Upland	World; broad range of prop.	USA / world; Upland or similar
Frequency	12 times/year	4 times/year	4 times/year
Number of samples	2 samples	1 sample	4 / 5 samples



This project is co-funded by
the European Union and the
Common Fund for Commodities

Existing Round Trials – Attributes

(2)

Critères des tests existants



Attribute	USDA HVI Checktest	Bremen Round Trial	CSITC Round Trial
Aim	Information for the laboratory	Information for the laboratory	Official laboratory evaluation and detailed analysis for the laboratory
Evaluation of	Laboratory average	Laboratory average	Laboratory average and all single data
Evaluation of Trueness	Yes	Yes	Yes
Evaluation of precision	No	No	Yes
Detailed evaluation	No	No	Yes
Official grading result	No	No	Yes

Plan of presentation Plan de présentation



- Existing tests
- CSITC RT
- Data for one instrument
- Evaluation principle
- Charts
- Influences
- Example
- Another example
- On the long run
- Tests actuels
- CSITC RT
- Données d'un instrument
- Principe d'évaluation
- Graphes
- Influences
- Exemple
- Autre exemple
- Dans le temps

CSITC Round Trial Configuration Configuration du test CSITC



	Cotton 1	Cotton 2	Cotton 3	Cotton 4		Cotton 5
day 1	6 tests	6 tests	6 tests	6 tests		<i>6 tests</i>
day 2	6 tests	6 tests	6 tests	6 tests		<i>6 tests</i>
day 3	6 tests	6 tests	6 tests	6 tests		<i>6 tests</i>
day 4	6 tests	6 tests	6 tests	6 tests		<i>6 tests</i>
day 5	6 tests	6 tests	6 tests	6 tests		<i>6 tests</i>
Sub Total	30 tests	30 tests	30 tests	30 tests		<i>30 tests</i>
Total	150 tests for each Round Trial					

- Cotton 1 to cotton 4 are used to evaluate laboratories reliably
- Cotton 5 offers the chance to include cottons with different behaviour / from different origins
- Les coton 1 à 4 servent à évaluer la performance des laboratoires
- Le coton 5 permet d'inclure d'autres types de cotons ou d'autres origines

Plan of presentation Plan de présentation



- Existing tests
- CSITC RT
- Data for one instrument
- Evaluation principle
- Charts
- Influences
- Example
- Another example
- On the long run
- Tests actuels
- CSITC RT
- Données d'un instrument
- Principe d'évaluation
- Graphes
- Influences
- Exemple
- Autre exemple
- Dans le temps

Results for one instrument Résultats d'un instrument



CSITC Round Test		Cotton 1					
	Test	Micronaire	Strength	Length	Uniformity	Color Rd	Color +b
Day 1	1	4.8	27.25	0.951	79.85	77.7	8.6
Temp	2	4.85	27.8	0.958	80.1	77.65	8.6
22.2	3	4.88	27.8	1.011	81.1	77.5	8.7
RH	4	4.87	27.8	0.999	81.8	76.3	8.75
65	5	4.92	27.75	0.997	80.7	76.4	8.85
64.8	6	4.85	27.95	1.007	80.4	76.75	9.05
Day 2	1	4.8	27.5	0.953	81.1	77.8	8.6
Temp	2	4.85	27.5	0.996	81.15	76.55	8.85
22.2	3	4.85	28.6	1.011	79.9	77	8.55
RH	4	4.78	27.65	1.014	80.65	76.9	8.95
64.8	5	4.8	28.15	1.009	81.1	77.5	8.8
64.8	6	4.93	27.75	1.008	81.15	77.8	8.75
Day 3	1	4.8	28.95	0.991	80.55	78.8	8.6
Temp	2	4.77	28.1	1	80.95	77.55	8.8
22.1	3	4.8	27.45	1.033	81.3	77.75	8.75
RH	4	4.85	27.9	1.015	81.15	76.75	8.55
65	5	4.83	28.15	1.018	81.35	78.2	8.6
64.9	6	4.82	27.6	1.033	81	78.9	8.6
Day 4	1	4.88	28.55	1.014	79.85	77.5	8.75
Temp	2	4.83	28.55	1.026	81.45	77.3	8.7
22.1	3	4.8	28.25	1.002	81.05	77.55	8.55
RH	4	4.88	28.55	0.992	81.5	77.25	8.55
64.9	5	4.83	27.8	0.991	80.8	78.7	8.7
64.9	6	4.8	27.55	1.024	80.8	77.3	8.7
Day 5	1	4.8	28.95	0.995	81	77.5	8.75
Temp	2	4.86	27.5	1.033	81.5	78.15	8.55
21.9	3	4.83	27.8	1.033	81.35	77.9	8.55
RH	4	4.82	28.5	0.971	80.6	77.6	8.65
64.9	5	4.78	27.7	0.988	79.65	77	8.75
64.9	6	4.84	28.7	1	80.4	77.65	8.65

CSITC Round Test		Cotton 2					
	Test	Micronaire	Strength	Length	Uniformity	Color Rd	Color +b
Day 1	1	4.23	30.45	1.024	83.15	76.9	12.35
Temp	2	4.23	30.45	1.022	83.15	76.9	12.35
22.2	3	4.23	30.45	1.022	83.15	76.9	12.35
RH	4	4.27	30.2	1.022	83.15	76.9	12.4
65	5	4.27	30.2	1.022	83.15	76.9	12.4
64.8	6	4.26	30.2	1.022	83.15	76.9	12.4
Day 2	1	4.23	30.45	1.022	83.05	76.9	12.35
Temp	2	4.23	30.45	1.021	83.05	76.9	12.35
22.2	3	4.23	30.45	1.021	83.05	76.9	12.35
RH	4	4.23	30.45	1.022	83.05	76.9	12.35
64.8	5	4.23	30.45	1.022	83.05	76.9	12.35
64.8	6	4.26	30.2	1.021	83.05	76.9	12.4
Day 3	1	4.23	30.45	1.021	83.15	76.9	12.35
Temp	2	4.23	30.45	1.021	83.15	76.9	12.35
22.1	3	4.23	30.45	1.021	83.15	76.9	12.35
RH	4	4.23	30.45	1.022	83.15	76.9	12.35
65	5	4.23	30.45	1.022	83.15	76.9	12.35
64.8	6	4.24	30.45	1.021	83.15	76.9	12.4
Day 4	1	4.23	30.45	1.021	83.05	76.9	12.35
Temp	2	4.23	30.45	1.021	83.05	76.9	12.35
22.1	3	4.23	30.45	1.021	83.05	76.9	12.35
RH	4	4.23	30.45	1.022	83.05	76.9	12.35
65	5	4.23	30.45	1.022	83.05	76.9	12.35
64.9	6	4.23	30.45	1.021	83.05	76.9	12.4
Day 5	1	4.23	30.45	1.021	83.15	76.9	12.35
Temp	2	4.23	30.45	1.021	83.15	76.9	12.35
22.1	3	4.23	30.45	1.021	83.15	76.9	12.35
RH	4	4.23	30.45	1.022	83.15	76.9	12.35
65	5	4.23	30.45	1.022	83.15	76.9	12.35
64.9	6	4.23	30.45	1.021	83.15	76.9	12.4

CSITC Round Test		Cotton 4					
	Test	Micronaire	Strength	Length	Uniformity	Color Rd	Color +b
Day 1	1	4.23	30.45	1.021	83.15	76.9	12.35
Temp	2	4.23	30.45	1.021	83.15	76.9	12.35
22.1	3	4.23	30.45	1.021	83.15	76.9	12.35
RH	4	4.23	30.45	1.022	83.15	76.9	12.35
65	5	4.23	30.45	1.022	83.15	76.9	12.35
64.9	6	4.23	30.45	1.021	83.15	76.9	12.4
Day 2	1	4.23	30.45	1.021	83.05	76.9	12.35
Temp	2	4.23	30.45	1.021	83.05	76.9	12.35
22.1	3	4.23	30.45	1.021	83.05	76.9	12.35
RH	4	4.23	30.45	1.022	83.05	76.9	12.35
65	5	4.23	30.45	1.022	83.05	76.9	12.35
64.9	6	4.23	30.45	1.021	83.05	76.9	12.4
Day 3	1	4.23	30.45	1.021	83.15	76.9	12.35
Temp	2	4.23	30.45	1.021	83.15	76.9	12.35
22.1	3	4.23	30.45	1.021	83.15	76.9	12.35
RH	4	4.23	30.45	1.022	83.15	76.9	12.35
65	5	4.23	30.45	1.022	83.15	76.9	12.35
64.9	6	4.23	30.45	1.021	83.15	76.9	12.4
Day 4	1	4.23	30.45	1.021	83.05	76.9	12.35
Temp	2	4.23	30.45	1.021	83.05	76.9	12.35
22.1	3	4.23	30.45	1.021	83.05	76.9	12.35
RH	4	4.23	30.45	1.022	83.05	76.9	12.35
65	5	4.23	30.45	1.022	83.05	76.9	12.35
64.9	6	4.23	30.45	1.021	83.05	76.9	12.4
Day 5	1	4.23	30.45	1.021	83.15	76.9	12.35
Temp	2	4.23	30.45	1.021	83.15	76.9	12.35
22.1	3	4.23	30.45	1.021	83.15	76.9	12.35
RH	4	4.23	30.45	1.022	83.15	76.9	12.35
65	5	4.23	30.45	1.022	83.15	76.9	12.35
64.9	6	4.23	30.45	1.021	83.15	76.9	12.4

CSITC Round Test		Cotton 5 (unofficial)					
	Test	Micronaire	Strength	Length	Uniformity	Color Rd	Color +b
Day 1	1	4.23	30.45	1.021	83.15	76.9	12.35
Temp	2	4.23	30.45	1.021	83.15	76.9	12.35
22.1	3	4.23	30.45	1.021	83.15	76.9	12.35
RH	4	4.23	30.45	1.022	83.15	76.9	12.35
65	5	4.23	30.45	1.022	83.15	76.9	12.35
64.9	6	4.23	30.45	1.021	83.15	76.9	12.4
Day 2	1	4.23	30.45	1.021	83.05	76.9	12.35
Temp	2	4.23	30.45	1.021	83.05	76.9	12.35
22.1	3	4.23	30.45	1.021	83.05	76.9	12.35
RH	4	4.23	30.45	1.022	83.05	76.9	12.35
65	5	4.23	30.45	1.022	83.05	76.9	12.35
64.9	6	4.23	30.45	1.021	83.05	76.9	12.4
Day 3	1	4.23	30.45	1.021	83.15	76.9	12.35
Temp	2	4.23	30.45	1.021	83.15	76.9	12.35
22.1	3	4.23	30.45	1.021	83.15	76.9	12.35
RH	4	4.23	30.45	1.022	83.15	76.9	12.35
65	5	4.23	30.45	1.022	83.15	76.9	12.35
64.9	6	4.23	30.45	1.021	83.15	76.9	12.4
Day 4	1	4.23	30.45	1.021	83.05	76.9	12.35
Temp	2	4.23	30.45	1.021	83.05	76.9	12.35
22.1	3	4.23	30.45	1.021	83.05	76.9	12.35
RH	4	4.23	30.45	1.022	83.05	76.9	12.35
65	5	4.23	30.45	1.022	83.05	76.9	12.35
64.9	6	4.23	30.45	1.021	83.05	76.9	12.4
Day 5	1	4.23	30.45	1.021	83.15	76.9	12.35
Temp	2	4.23	30.45	1.021	83.15	76.9	12.35
22.1	3	4.23	30.45	1.021	83.15	76.9	12.35
RH	4	4.23	30.45	1.022	83.1		

Results for one instrument Résultats d'un instrument



Vers.: 3.1.11 GL 2010-1 LABORATORY EVALUATION P. 1 11.03.2010

Laboratory Evaluation Lab.: 026-02
- Combined Properties -
According to ICAC CSITC Task Force Recommendations
Round Trial No.: GL 2010-1

	Lab. No.	Evaluation Combined Prop.
Your Evaluation	026-02	0.61

Statistics		Evaluation Combined Prop.
Average		0.58
Median		0.54
Best Lab.		0.20
Worst Lab.		1.96

- table is divided into 2 pages -

No.	Lab. No.	Evaluation Combined Prop.
1	063-01	0.20
2	071-01	0.20
3	060-01	0.26
4	069-07	0.28
5	083-04	0.29
6	083-03	0.30
7	026-01	0.32
8	017-02	0.35
9	069-02	0.36
10	009-07	0.36
11	037-03	0.36
12	040-01	0.36
13	077-01	0.37
14	027-02	0.37
15	016-02	0.38
16	059-06	0.38
17	082-01	0.39

Results for one instrument Résultats d'un instrument



Vers.: 3.1.11 GL 2010-1 LABORATORY EVALUATION P. 3 11.03.2010

Laboratory Evaluation Lab.: 026-02
- Graph of Combined Properties -
According to ICAC CSITC Task Force Recommendations
Round Trial No.: GL 2010-1

	Lab. No.	Evaluation Combined Prop.
Your Evaluation	026-02	0.61

Statistics		Evaluation Combined Prop.
Average		0.58
Median		0.54
Best Lab.		0.20
Worst Lab.		1.96

Evaluation Results - Combined Properties -

The x-axis shows midpoints of classes.
The evaluation results are entered based on the unrounded values.



Results for one instrument Résultats d'un instrument



Vers.: 3.1.11 GL 2010-1 LABORATORY EVALUATION P. 4 11.03.2010

Laboratory Evaluation Lab.: 026-02
- Single Properties -
According to ICAC CSITC Task Force Recommendations
Round Trial No.: GL 2010-1

Lab. No.	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color 4b
026-02	0.37	0.47	1.41	0.83	0.98	0.71

Statistics	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color 4b
Average	0.70	0.57	1.47	0.43	0.97	0.66
Min. Lab.	0.15	0.11	0.27	0.06	0.97	0.52
Max. Lab.	0.15	0.11	0.27	0.06	0.97	0.52
World Lab.	2.34	2.20	1.47	0.97	2.58	4.18

No.	Lab. No.	Evaluation Micronaire	Lab. No.	Evaluation Strength	Lab. No.	Evaluation Length	Lab. No.	Evaluation Uniformity	Lab. No.	Evaluation Color Rd	Lab. No.	Evaluation Color 4b
1	093-01	0.15	069-01	0.11	060-01	0.97	027-01	0.06	060-01	0.97	060-01	0.05
2	096-01	0.18	069-02	0.15	027-02	0.99	063-01	0.14	071-01	0.11	071-01	0.09
3	096-03	0.18	069-02	0.15	027-02	0.99	063-01	0.14	071-01	0.11	071-01	0.09
4	097-01	0.18	074-01	0.15	029-01	0.97	026-01	0.15	026-01	0.15	026-01	0.14
5	097-02	0.18	074-01	0.15	029-01	0.93	030-01	0.15	026-01	0.15	026-01	0.14
6	093-01	0.19	059-06	0.16	034-01	0.14	071-01	0.15	018-01	0.17	029-01	0.15
7	093-01	0.19	059-06	0.16	034-01	0.14	071-01	0.15	018-01	0.17	029-01	0.15
8	077-01	0.22	027-02	0.21	071-01	0.15	026-03	0.17	027-02	0.17	077-01	0.16
9	079-01	0.25	063-04	0.22	048-01	0.15	016-02	0.18	037-03	0.18	066-01	0.16
10	079-01	0.25	063-04	0.22	048-01	0.15	016-02	0.18	037-03	0.18	066-01	0.16
11	093-01	0.28	065-02	0.24	040-01	0.17	034-01	0.18	009-06	0.18	044-01	0.23
12	076-01	0.29	030-01	0.25	063-01	0.17	077-01	0.19	063-01	0.18	016-01	0.23
13	076-01	0.29	030-01	0.25	063-01	0.17	077-01	0.19	063-01	0.18	016-01	0.23
14	017-01	0.29	029-03	0.26	027-01	0.19	047-01	0.19	062-01	0.20	075-01	0.24
15	093-01	0.30	041-01	0.27	029-01	0.19	039-01	0.20	027-04	0.22	074-01	0.20
16	093-01	0.33	041-01	0.27	029-01	0.19	039-01	0.20	027-04	0.22	074-01	0.20
17	030-02	0.35	037-03	0.27	078-01	0.34	004-01	0.20	017-02	0.22	078-01	0.31
18	066-01	0.36	073-01	0.27	120-03	0.34	024-01	0.21	009-07	0.33	090-01	0.32
19	066-01	0.36	073-01	0.27	120-03	0.34	024-01	0.21	009-07	0.33	090-01	0.32
20	090-01	0.36	020-01	0.28	083-03	0.34	010-01	0.21	039-01	0.27	031-01	0.26
21	090-01	0.36	020-01	0.28	083-03	0.34	010-01	0.21	039-01	0.27	031-01	0.26
22	067-02	0.37	056-01	0.31	089-01	0.28	057-04	0.21	016-02	0.28	027-01	0.31
23	026-02	0.37	056-01	0.31	076-01	0.27	056-03	0.21	087-02	0.28	013-01	0.34
24	026-02	0.37	056-01	0.31	076-01	0.27	056-03	0.21	087-02	0.28	013-01	0.34
25	063-07	0.38	086-03	0.33	013-01	0.30	018-01	0.24	087-01	0.30	059-06	0.34
26	049-01	0.41	087-01	0.35	026-01	0.30	018-01	0.25	014-01	0.30	092-01	0.35
27	019-01	0.43	020-01	0.35	026-01	0.30	020-01	0.25	020-01	0.31	020-01	0.35
28	019-01	0.43	020-01	0.35	050-01	0.31	050-01	0.28	075-01	0.33	044-01	0.36
29	064-02	0.43	074-01	0.36	041-01	0.32	057-01	0.25	002-01	0.35	091-01	0.37
30	064-02	0.43	074-01	0.36	041-01	0.32	057-01	0.25	002-01	0.35	091-01	0.37
31	091-01	0.45	010-02	0.36	006-01	0.32	059-06	0.28	018-01	0.35	063-04	0.37
32	015-01	0.47	025-01	0.37	048-01	0.32	021-01	0.25	021-01	0.42	037-03	0.38
33	015-01	0.47	025-01	0.37	048-01	0.32	021-01	0.25	021-01	0.42	037-03	0.38



Results for one instrument Résultats d'un instrument




Vers.: 3.1.11 GL 2010-1 LABORATORY EVALUATION P. 6 11.03.2010

Laboratory Evaluation Lab.: 026-02
- Graph of Single Properties -
According to ICAC CSITC Task Force Recommendations
Round Trial No.: GL 2010-1

Lab. No.	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color 4b
026-02	0.37	0.47	1.41	0.83	0.98	0.71

Statistics	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color 4b
Average	0.70	0.57	1.47	0.43	0.97	0.66
Min. Lab.	0.15	0.11	0.27	0.06	0.97	0.52
Max. Lab.	0.15	0.11	0.27	0.06	0.97	0.52
World Lab.	2.34	2.20	1.47	0.97	2.58	4.18



Y-axis shows the number of observations.
The evaluation results are ordered based on the unsorted values.

This project is co-funded by the European Union and the Common Fund for Commodities

**Results for one instrument
Résultats d'un instrument**


Vers. 3.1.11 GL 2010-1 LABORATORY EVALUATION P. 7 11.03.2010

Performance of Laboratory 026-02

	Micronaire	Strength	Length	Uniformity	Color Rd	Color +b
Reference Values	4.492	29.015	1.1093	81.545	78.428	9.859
Cotton 1	4.290	32.916	1.1674	80.393	77.436	12.051
Cotton 2	4.307	27.894	1.1357	82.607	71.084	8.476
Cotton 3	5.069	28.725	1.1153	83.514	74.722	14.448
Cotton 4	4.142	29.720	1.1428	82.936	78.580	9.251
Cotton 5						
Laboratory Average of All Days	4.505	29.187	1.0973	80.777	80.427	9.443
Cotton 1	4.324	33.690	1.1623	82.707	78.563	11.653
Cotton 2	4.350	27.307	1.1217	81.823	72.867	8.233
Cotton 3	5.118	27.423	1.1137	83.257	76.320	14.110
Cotton 4	4.173	31.137	1.1380	82.467	80.300	8.923
Cotton 5						
Rel. Distance to Reference	0.019	0.171	-0.019	-0.773	1.694	-0.444
Cotton 1	0.033	0.774	-0.061	-0.674	1.127	-0.444
Cotton 2	0.043	-0.587	-0.040	-0.783	1.783	-0.243
Cotton 3	0.059	-1.301	-0.017	-0.258	1.598	-0.336
Cotton 4	0.031	1.417	-0.0048	-0.469	1.720	-0.328
Cotton 5						
Mean Absolute Distance to Reference (Cotton 1 - 4 only)	0.037	0.708	0.0082	0.625	1.626	0.356
Scale Factor	0.10	1.50	0.02	1.00	1.50	0.50
Summary Evaluation for Each Property	0.37	0.47	0.41	0.63	1.08	0.71
Relevance of Property	1.00	1.00	1.00	1.00	1.00	1.00
Summary Evaluation of All Properties			0.61			

Number of outliers in submitted test data:

Parameter	Allowed Range	Number of total outliers in your submitted test data
Micronaire	1.5 to 8	0
Strength	15 to 60 g/tex	0
Length	0 to 1.7 inches	0
Uniformity	60 to 100	0
Color Rd	40 to 90	0
Color +b	4 to 18	0
Total number		0





This project is co-funded by the European Union and the Common Fund for Commodities



Results for one instrument Résultats d'un instrument



Detailed Analysis									
Precision Analysis									
Comments									
Microsare									
Reference Values for Evaluation									
Typical In-Lab. Variation (measuring)									
In-Lab. Variation (True Lab.)									
Comments									
Strength									
Reference Values for Evaluation									
Typical In-Lab. Variation (measuring)									
In-Lab. Variation (True Lab.)									
Comments									
Length									
Reference Values for Evaluation									
Typical In-Lab. Variation (measuring)									
In-Lab. Variation (True Lab.)									
Comments									
Uniformity									
Reference Values for Evaluation									
Typical In-Lab. Variation (measuring)									
In-Lab. Variation (True Lab.)									
Comments									
Color Rd									
Reference Values for Evaluation									
Typical In-Lab. Variation (measuring)									
In-Lab. Variation (True Lab.)									
Comments									
Color #B									
Reference Values for Evaluation									
Typical In-Lab. Variation (measuring)									
In-Lab. Variation (True Lab.)									
Comments									





This project is co-funded by the European Union and the Common Fund for Commodities



Plan of presentation Plan de présentation



- Existing tests
- CSITC RT
- Data for one instrument
- Evaluation principle
- Charts
- Influences
- Example
- Another example
- On the long run
- Tests actuels
- CSITC RT
- Données d'un instrument
- Principe d'évaluation
- Graphes
- Influences
- Exemple
- Autre exemple
- Dans le temps





This project is co-funded by
the European Union and the
Common Fund for Commodities




Evaluation of Systematic Deviations Evaluation des écarts systématiques



- Laboratory 1 – Length results:

- Trueness is good La justesse est acceptable
- The results of the single days are consistent Résultats par jour acceptables
- No actions necessary to improve Rien à améliorer



This project is co-funded by
the European Union and the
Common Fund for Commodities




Evaluation of Systematic Deviations Evaluation des écarts systématiques



- Laboratory 2 – Length results:

- For short cottons, the deviations from the reference results are too high
- The results of the single days are extremely consistent



Pour les coton courts, les écarts avec les résultats de référence sont trop grands.
Les résultats par jour sont extrêmement reproductibles.




This project is co-funded by
the European Union and the
Common Fund for Commodities



Evaluation of Systematic Deviations Evaluation des écarts systématiques



- Laboratory 3 – Length results:
 - The trueness of the results is in a tolerable range
 - The results between the single days are totally deviating from each other



La justesse des résultats est dans les tolérances.

Les résultats sont différents chaque jour de tests.



This project is co-funded by
the European Union and the
Common Fund for Commodities



Plan of presentation Plan de présentation



- Existing tests
- CSITC RT
- Data for one instrument
- Evaluation principle
- Charts
- Influences
- Example
- Another example
- On the long run
- Tests actuels
- CSITC RT
- Données d'un instrument
- Principe d'évaluation
- Graphes
- Influences
- Exemple
- Autre exemple
- Dans le temps

This project is co-funded by the European Union and the Common Fund for Commodities



**Example
Exemple**

Cotton Testing in Africa
CSITC-Project

Performance of Laboratory 026-02						
	Micronaire	Strength	Length	Uniformity	Color Rd	Color +b
Reference Values	Cotton 1	4,492	29,015	1,1093	81,549	78,432
	Cotton 2	4,290	32,916	1,1874	83,393	77,436
	Cotton 3	4,307	27,894	1,1357	82,807	71,084
	Cotton 4	5,059	28,725	1,1153	83,514	74,722
	Cotton 5	4,142	29,720	1,1428	82,936	78,580
Laboratory Average of All Days	Cotton 1	4,505	29,187	1,0973	80,777	80,427
	Cotton 2	4,324	33,690	1,1823	82,707	78,583
	Cotton 3	4,350	27,307	1,1217	81,823	72,887
	Cotton 4	5,118	27,423	1,1137	83,257	76,320
	Cotton 5	4,173	31,137	1,1380	82,467	80,300
Rel. Distance to Reference	Cotton 1	0,013	0,171	-0,0119	-0,773	1,994
	Cotton 2	0,033	0,774	-0,0051	-0,686	1,127
	Cotton 3	0,043	-0,587	-0,0140	-0,783	1,783
	Cotton 4	0,059	-1,301	-0,0017	-0,258	1,598
	Cotton 5	0,031	1,417	-0,0048	-0,469	1,720
Mean Absolute Distance to Reference (Cotton 1 - 4 only)		0,037	0,708	0,0082	0,625	1,626
Scale Factor		0,10	1,50	0,02	1,00	1,50
Summary Evaluation for Each Property		0,37	0,47	0,41	0,63	1,08
Relevance of Property		1,00	1,00	1,00	1,00	1,00
Summary Evaluation of All Properties					0,61	

This project is co-funded by the European Union and the Common Fund for Commodities




**Example
Exemple**

Cotton Testing in Africa
CSITC-Project

Laboratory Evaluation	Lab.: 026-02
- Combined Properties -	
According to ICAC CSITC Task Force Recommendations	
Round Trial No.: GL 2010-1	
Your Evaluation	026-02
Statistics	Evaluation Combined Prop.
Average	0,58
Median	0,54
Best Lab.	0,20
Worst Lab	1,96
No.	Lab. No.
41	021-01
42	067-01
43	039-01
44	040-01
45	079-01
46	046-01
47	076-01
48	010-02
49	091-01
50	086-02
51	077-02
52	030-01
53	003-01
54	019-01
55	074-01
56	002-01
57	089-01
58	026-02
59	000-01

All labs average
Moyenne de tous les laboratoires

Your instrument
Votre instrument



This project is co-funded by the European Union and the Common Fund for Commodities

cirad

Example Exemple

Laboratory Evaluation Lab.: 026-02

- Single Properties -

According to ICAC CSITC Task Force Recommendations

Round Trial No.: GL 2010-1

Your Evaluation

Lab. No.	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color +b
026-02	0.37	0.47	0.41	0.63	1.08	0.71

Statistics

Statistics	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color +b
Average	0.70	0.57	0.47	0.43	0.67	0.66
Median	0.58	0.47	0.39	0.46	0.51	0.49
Best Lab.	0.15	0.11	0.07	0.06	0.07	0.05
Worst Lab.	2.34	2.20	1.47	0.97	2.58	4.18

ATTENTION !!!

All labs average
Moyenne de tous les laboratoires

Your instrument
Votre instrument

This project is co-funded by the European Union and the Common Fund for Commodities

cirad

Example Exemple

Laboratory Evaluation Lab.: 026-02

- Single Properties -

According to ICAC CSITC Task Force Recommendations

Round Trial No.: GL 2010-1

Your Evaluation

Lab. No.	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color +b
026-02	0.37	0.47	0.41	0.63	1.08	0.71

Statistics

Statistics	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color +b
Average	0.70	0.57	0.47	0.43	0.67	0.66
Median	0.58	0.47	0.39	0.36	0.51	0.49
Best Lab.	0.15	0.11	0.07	0.06	0.07	0.05
Worst Lab.	2.34	2.20	1.47	0.97	2.58	4.18

No. Lab. No. Evaluation Color Rd

61	030-01	0.85
62	027-01	0.86
63	088-01	0.86
64	059-06	0.91
65	072-01	0.94
66	023-01	0.96
67	074-01	0.99
68	089-01	1.00
69	079-01	1.03
70	061-01	1.03
71	029-01	1.04
72	059-05	1.05
73	086-01	1.06
74	099-03	1.07
75	026-02	1.08
76	056-01	1.14
77	047-01	1.17
78	057-01	1.35
79	044-01	1.35
80	076-01	1.38
81	038-01	1.46
82	050-01	1.58
83	056-01	1.69
84	064-01	1.69
85	033-01	2.31
86	078-02	2.39
87	078-01	2.58

ATTENTION !!!

All labs average
Moyenne de tous les laboratoires

Your instrument
Votre instrument

This project is co-funded by the European Union and the Common Fund for Commodities

cirad

Example Exemple

Laboratory Evaluation Lab.: 026-02

- Single Properties -

According to ICAC CSITC Task Force Recommendations

Round Trial No.: GL 2010-1

Your Evaluation

Lab. No.	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color +b
026-02	0.37	0.47	0.41	0.63	1.08	0.71

Statistics

Statistics	Evaluation Micronaire	Evaluation Strength	Evaluation Length	Evaluation Uniformity	Evaluation Color Rd	Evaluation Color +b
Average	0.70	0.57	0.47	0.43	0.67	0.66
Median	0.58	0.47	0.39	0.36	0.51	0.49
Best Lab.	0.15	0.11	0.07	0.06	0.07	0.05
Worst Lab.	2.34	2.20	1.47	0.97	2.58	4.18

No. Lab. No. Evaluation Color Rd

61	030-01	0.85
62	027-01	0.86
63	088-01	0.86
64	059-06	0.91
65	072-01	0.94
66	023-01	0.96
67	074-01	0.99
68	089-01	1.00
69	079-01	1.03
70	061-01	1.03
71	029-01	1.04
72	059-05	1.05
73	086-01	1.06
74	099-03	1.07
75	026-02	1.08
76	056-01	1.14
77	047-01	1.17
78	057-01	1.35
79	044-01	1.35
80	076-01	1.38
81	038-01	1.46
82	050-01	1.58
83	056-01	1.69
84	064-01	1.69
85	033-01	2.31
86	078-02	2.39
87	078-01	2.58


ATTENTION !!!

All labs average
Moyenne de tous les laboratoires

Your instrument
Votre instrument

Evaluation Results Color Rd

Evaluation Result	No. of Laboratories
0.0	15
0.5	18
0.6	15
0.7	12
0.8	8
0.9	6
1.0	4
1.1	3
1.2	2
1.3	1
1.4	1
1.5	1
1.6	1
1.7	1
1.8	1
1.9	1
2.0	1
2.1	1
2.2	1
2.3	1
2.4	1
2.5	1



**Another example
Autre exemple**

This project is co-funded by the European Union and the Common Fund for Commodities

Cotton Testing in Africa

	Strength						
	Cotton 1	Cotton 2	Cotton 3	Cotton 4	Average	Cotton 5	Remark
Reference Values for Evaluation	29.015	32.916	27.894	28.725	29.720		
Typical In-Lab. Variation (Median)	SD 0.480	SD 0.443	SD 0.428	SD 0.469	SD 0.455	SD 0.458	
In-Lab. Variation (Your Lab.)	SD 0.524	SD 0.477	SD 0.488	SD 0.292	SD 0.583	SD 0.590	
	between different days with each 6 tests	between single tests on one day	between all tests on different days	between different days with each 6 tests	between single tests on one day	between all tests on different days	
	SD 0.565	SD 0.684	SD 0.555	SD 0.524	SD 1.107	SD 0.488	
	0.565	0.684	0.555	0.524	1.107	0.488	

ATTENTION !!!

All labs average
Moyenne de tous les laboratoires



Your instrument
Votre instrument

Plan of presentation Plan de présentation




- Existing tests
- CSITC RT
- Data for one instrument
- Evaluation principle
- Charts
- Influences
- Example
- Another example
- On the long run
- Tests actuels
- CSITC RT
- Données d'un instrument
- Principe d'évaluation
- Graphes
- Influences
- Exemple
- Autre exemple
- Dans le temps

On the long run... Dans le temps ...



On the long run... Dans le temps ...



Plan of presentation Plan de présentation



- Existing tests
- CSITC RT
- Data for one instrument
- Evaluation principle
- Charts
- Influences
- Example
- Another example
- On the long run
- Tests actuels
- CSITC RT
- Données d'un instrument
- Principe d'évaluation
- Graphes
- Influences
- Exemple
- Autre exemple
- Dans le temps



On the long run... Dans le temps ...



- Use of csitc.org
- Utilisation du csitc.org

[CSITC-RoundTrial-instructions-2s.pdf](#)



On the long run... Dans le temps ...



Inter-laboratory test within the Region

- Activity of the RTC-AOC
- Same configuration as the international CSITC test
- Cottons from the Region
- No certificate
- However a diagnostic of the laboratory performances

Tests inter-laboratoires dans la Région

- Activité du CTR-AOC
- Même configuration que le test CSITC international
- Cotons de la Région
- Pas de certificat
- Mais un diagnostic des performances des laboratoires

On the long run... Dans le temps ...



Round test: every three months
→ importance of retests

Also a normal activity of the RTC-AOC:
• Laboratories send samples to the RTC which test them and compare their results to yours for a diagnostic
• Periodicity: every week

Tests inter-laboratoires : tous les 3 mois
→ importance des retests

Egalement une activité normale du CTR-AOC :
• Les laboratoires envoient des échantillons au CTR qui les teste et compare ses résultats aux vôtres pour un diagnostic
• Fréquence : toutes les semaines



Thank you for your attention
Merci de votre attention